



Torlon® Chemical Resistance

CHEMICAL PROPERTIES	COMMENTS
Acids, Weak (acetic, dilute HCl)	Acceptable Service
Acids, Strong (conc. HCl or sulfuric)	Limited Service
Alkalies, Weak (dilute NaOH)	Limited Service
Alkalies, Strong (conc. NaOH)	Unacceptable
Hydrocarbons, Aromatic (toluene)	Acceptable Service
Hydrocarbons, Aliphatic (gasoline)	Acceptable Service
Ketones, Esters (acetone)	Acceptable Service
Ethers (diethyl ether, THF)	Acceptable Service
Chlorinated Solvents (methylene chloride)	Acceptable Service
Alcohols (methanol, anti-freeze)	Acceptable Service
Inorganic Salt Solutions (NaCl, KCl)	Acceptable Service
Continuous Sunlight	Limited Service
Steam	Unacceptable